

G. Barclay et al.
U.S.S.N. 10/083,675
Page 2

This listing of claims will replace all prior versions of claims in the application.

Claims 1-123. (cancelled)

Claim 124. (previously presented) A method for preparing a photoresist composition, comprising:

a) providing a polymer by a polymerization reaction that comprises adding over the substantial course of the polymerization reaction one or more incorporated polymerization reagents to a reaction mixture,

wherein multiple incorporated polymerization reagents are reacted, and the incorporated polymerization reagent with the second fastest reaction rate relative to the other incorporated polymerization reagents is added to the reaction mixture over the substantial course of the polymerization reaction; and

b) admixing the polymer with a photoactive component.

Claim 125. (previously presented) A method of preparing a photoresist composition, comprising:

a) providing a polymer that comprises units that comprise a polymerized maleic anhydride group, the polymer provided by a polymerization reaction that comprises adding maleic anhydride over the substantial course of the polymerization reaction to a reaction mixture; and

b) admixing the polymer with a photoactive component.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 3

Claim 126. (currently amended) A method of preparing a photoresist composition, comprising:

- a) providing a polymer that comprises units that comprise a polymerized acrylate group, the polymer provided by a polymerization reaction that comprises adding ~~a~~ an acrylate compound over the substantial course of the polymerization reaction to a reaction mixture; and
- b) admixing the polymer with a photoactive component.

Claim 127. (previously presented) A method of preparing a photoresist composition, comprising:

- a) providing a polymer that comprises units that comprise a lactone moiety, the polymer provided by a polymerization reaction that comprises adding a compound comprising a lactone moiety over the substantial course of the polymerization reaction to a reaction mixture; and
- b) admixing the polymer with a photoactive component.

Claim 128. (currently amended) A method for preparing a photoresist composition, comprising:

- a) providing a polymer by a polymerization reaction that comprises adding over the substantial course of the polymerization reaction one or more incorporated polymerization reagents to a reaction mixture;
- b) admixing the polymer with a photoactive component; and
- c) applying on a substrate a coating layer of a photoresist composition comprising the polymer and photoactive component, exposing the photoresist layer to radiation having a wavelength of less than about 300 nm and developing the exposed the photoresist layer to yield a relief image.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 4

Claim 129. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein multiple incorporated polymerization reagents are reacted, and the incorporated polymerization reagent with the fastest reaction rate relative to the other incorporated polymerization reagents is added to the reaction mixture over the substantial course of the polymerization reaction.

Claim 130. (currently amended) The method of any one of claims 124, 125, 126, 127 or 128 wherein multiple incorporated polymerization reagents are reacted, and the incorporated polymerization reagent with the second fastest reaction rate relative to the other incorporated polymerization reagents is added to the reaction mixture over the substantial course of the polymerization reaction.

Claim 131. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein multiple incorporated polymerization reagents are reacted, and the incorporated polymerization reagent with the slowest fastest reaction rate relative to the other incorporated polymerization reagents is present in the reaction mixture at the start of the polymerization reaction and is not added to the reaction mixture over the substantial course of the polymerization reaction.

Claim 132. (previously presented) The method of claim 126 wherein the acrylate compound comprises a photoacid-labile ester.

Claim 133. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein a reaction mixture that contains one or more polymerization reagents is initially provided at the start of the polymerization reaction, and one or more additional polymerization reagents are added to the reaction mixture over the substantial course of the polymerization reaction.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 5

Claim 134. (previously presented) The method of claim 133 wherein the reaction mixtures comprises an optionally substituted carbon alicyclic compound or an optionally substituted heteroalicyclic compound at the start of the polymerization reaction.

Claim 135. (previously presented) The method of claim 133 wherein the reaction mixtures comprises an optionally substituted norbornene compound at the start of the polymerization reaction.

Claim 136. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein each incorporated polymerization reagent is added to a reaction mixture over the substantial course of the polymerization reaction.

Claim 137. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein the polymerization reaction is a free radical mediated reaction.

Claim 138. (previously presented) The method of any one of claims any one of claims 124, 125, 126, 127 or 128 wherein the polymerization reaction is an anionic, cationic or metal catalyzed reaction.

Claim 139. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein one or more of the polymerization reagents is selected from the group consisting of a fluorinated olefin, a carbon alicyclic compound, or a heteroalicyclic compound.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 6

Claim 140. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein one or more of the polymerization reagents is 2-methyladamantanyl methacrylate, 2-methyladamantanyl acrylate, maleic anhydride, norbornene, 3,4-dihydropyran, or tetrafluoroethylene.

Claim 141. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein each of the polymerization reagents is a non-aromatic compound.

Claim 142. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein one or more of the polymerization reagents is an aromatic compound.

Claim 143. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein one or more of the polymerization reagents comprises an optionally substituted phenyl or optionally substituted naphthyl moiety.

Claim 144. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein one or more polymerization reagents are added over at least about 80 percent of the duration of the polymerization reaction.

Claim 145. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein at least two polymerization reagents are added over the substantial course of the polymerization reaction.

Claim 146. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein a radical initiator compound is added over the substantial course of the polymerization reaction.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 7

Claim 147. (previously presented) The method of claim 146 wherein the initiator is added at a rate to maintain a substantially constant concentration of initiator within the reaction mixture over the substantial course of the polymerization reaction.

Claim 148. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein a reaction vessel is initially charged with one or more polymerization reagents, and one or more polymerization reagents having a faster reaction rate than the charged reagents are added to the reaction vessel over the substantial course of the polymerization reaction.


Claim 149. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein the polymer comprises photoacid labile repeat units that contain a tertiary alicyclic group.

Claim 150. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein the polymer comprises a polymerized fluorinated unsaturated monomer.

Claim 151. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein the polymer comprises a fused heteroalicyclic group having an oxygen ring member or sulfur ring member.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 8

Claim 152. (previously presented) The method of any one of claims 124, 125, 126, 127 or 128 wherein the polymer comprises a structure of the following formula:



wherein X, Y and Z are each independently carbon, oxygen or sulfur, with at least one of X, Y or Z being oxygen or sulfur, and preferably no more than two of X, Y and Z being oxygen or sulfur;

Q represents an optionally substituted carbon alicyclic group fused to the polymer backbone;

p and r are the mole fractions of the respective units and each of p and r is greater than zero.

Claim 153. (currently amended) The method of any one of claims 124, 125, 126, 127 or 128 wherein the composition comprising the polymer and photoactive component is a chemically-amplified positive-acting resist.

Claim 154. (currently amended) The method of any one of claims 124, 125, 126, 127 or 128 wherein the composition comprising the polymer and photoactive component is a negative-acting resist.

Claim 155. (currently amended) The method of any one of claims 124, 125, 126 or 127 further comprising applying on a substrate a coating layer of the photoresist composition comprising the polymer and photoactive component ~~on a substrate~~; exposing the

G. Barclay et al.
U.S.S.N. 10/083,675
Page 9

photoresist coating layer to patterned activating radiation; and developing the exposed photoresist coating layer to provide a resist relief image.

Claim 156. (previously presented) The method of claim 155 wherein the photoresist layer is exposed with radiation having a wavelength of less than about 300 nm.

Claim 157. (previously presented) The method of claim 155 wherein the photoresist layer is exposed with radiation having a wavelength of less than about 200 nm.

Claim 158. (previously presented) The method of claim 128 wherein the photoresist layer is exposed with radiation having a wavelength of less than about 200 nm.

Claim 159. (previously presented) The method of claim 155 wherein the photoresist layer is exposed with radiation having a wavelength of about 193 nm.

Claim 160. (previously presented) The method of claim 128 wherein the photoresist layer is exposed with radiation having a wavelength of about 193 nm.

Claim 161. (previously presented) The method of claim 155 wherein the substrate is a microelectronic wafer.

Claim 162. (previously presented) The method of claim 155 wherein the substrate is a microelectronic wafer.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 10

Claim 163. (previously presented) A method of forming a photoresist relief image, comprising:

- (a) applying on a substrate a coating layer of a photoresist comprising a photoactive component and a polymer obtainable by adding over the substantial course of a polymerization reaction one or more incorporated polymerization reagents to a reaction mixture; and
- (b) exposing the photoresist layer to radiation having a wavelength of less than about 300 nm and developing the exposed the photoresist layer to yield a relief image.

Claim 164. (previously presented) The method of claim 163 wherein the photoresist layer is exposed with radiation having a wavelength of less than about 200 nm.

Claim 165. (previously presented) The method of claim 163 wherein the photoresist layer is exposed with radiation having a wavelength of about 193 nm.

Claim 166. (previously presented) The method of claim 163 wherein multiple incorporated polymerization reagents are reacted, and the incorporated polymerization reagent with the fastest reaction rate relative to the other incorporated polymerization reagents is added to the reaction mixture over the substantial course of the polymerization reaction.

Claim 167. (previously presented) The method of claim 163 wherein multiple incorporated polymerization reagents are reacted, and the incorporated polymerization reagent with the second fastest reaction rate relative to the other incorporated polymerization reagents is added to the reaction mixture over the substantial course of the polymerization reaction.

G. Barclay et al.
U.S.S.N. 10/083,675
Page 11

Claim 168. (previously presented) The method of claim 163 wherein multiple incorporated polymerization reagents are reacted, and the incorporated polymerization reagent with the slowest fastest reaction rate relative to the other incorporated polymerization reagents is present in the reaction mixture at the start of the polymerization reaction and is not added to the reaction mixture over the substantial course of the polymerization reaction.

Claim 169. (previously presented) The method of claim 163 wherein the polymer is obtained by adding over the substantial course of a polymerization reaction one or more incorporated polymerization reagents to a reaction mixture.

Claim 170. (previously presented) The method of claim 163 wherein the polymer is obtained by adding over the substantial course of a polymerization reaction one or more incorporated polymerization reagents to a reaction mixture.

Claim 171. (previously presented) The method of claim 163 wherein maleic anhydride is added to the reaction mixture over the substantial course of the polymerization reaction.

Claim 172. (previously presented) The method of claim 163 wherein an acrylate compound is added to the reaction mixture over the substantial course of the polymerization reaction.

Claim 173. (previously presented) The method of claim 172 wherein the acrylate compound comprises a photoacid-labile ester.